

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification: <sup>7</sup> A61F 13/15, D04H 3/16, B65H 45/06, D04H 13/00	A1	(11) International Publication Number: WO 00/66057	(43) International Publication Date: 9 November 2000 (09.11.00)
--	----	---	--

(21) International Application Number:	PCT/US00/10758
(22) International Filing Date:	21 April 2000 (21.04.00)
(30) Priority Data:	60/132,028 09/538,744 30 April 1999 (30.04.99) 30 March 2000 (30.03.00) US US
(71) Applicant:	KIMBERLY-CLARK WORLDWIDE, INC. [US/US]: 401 North Lake Street, Necedah, WI 54956 (US).
(72) Inventors:	WHITE, Edward, Jason; 12206 Aronimink Point, Knoxville, TN 37922 (US). BROWN, Kurtis, Lee; 700 Rhodes Creek Trail, Alpharetta, GA 30004 (US). CONRAD, John, Herbert; 625 Briars Bend, Alpharetta, GA 30004 (US). GERNDT, Robert, James; 9158 Branch Valley Way, Roswell, GA 30076 (US). MALDONADO, Jose, Enrique; 11101 Lexington Farm Drive, Alpharetta, GA 30004 (US).
(74) Agents:	NORRIS, Roland, W.; Pauley Petersen Kinne & Fejer, Suite 365, 2800 West Higgins Road, Hoffman Estates, IL 60195 (US) et al.
(81) Designated States:	AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, GR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
	Published With international search report.

(S4) Title: MATERIALS HAVING Z-DIRECTION FIBERS AND FOLDS AND METHOD FOR PRODUCING SAME

(57) Abstract

A method for producing a material having z-direction waves in which a layer of continuous fibers is conveyed on a first moving surface, resulting in formation of a plurality of z-direction loops in the fibers giving loft to the material and a wave pattern producing ridges on both major surfaces of the resultant nonwoven web. The method permits easy real time adjustment of manufacturing parameters to produce a variety of materials. The method further produces lofty nonwovens at a commercially viable rate.



Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

FOR THE PURPOSES OF INFORMATION ONLY

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	MT	Malta	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Cote d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CN	China	KR	Republic of Korea	PL	Poland		
CU	Cuba	KZ	Kazakhstan	PT	Portugal		
CZ	Czech Republic	LC	Saint Lucia	RO	Romania		
DE	Germany	LI	Liechtenstein	RU	Russian Federation		
DK	Denmark	LK	Sri Lanka	SD	Sudan		
EE	Estonia	LR	Liberia	SE	Sweden		
				SG	Singapore		

# MATERIALS HAVING Z-DIRECTION FIBERS AND FOLDS AND METHOD FOR PRODUCING SAME

## BACKGROUND OF THE INVENTION

### Field of the invention

This invention relates to a method for producing materials, including films

and nonwovens, having z-direction folds or ridges on at least one surface of the material.

This invention further relates to a lofty, nonwoven material produced from continuous fibers

in which the lofty character of the nonwoven material is the result of the fibers comprising

the web having a z-direction orientation, whereby a plurality of ridges or folds are formed

on at least one surface of the nonwoven web. These materials are particularly suitable for

use in a broad range of applications including fluid management (surge), air and liquid

filtration, acoustic and thermal insulation, packing material, absorbents, and cleaning

materials. More particularly, these materials are suitable for use as surge, spacer layers,

filtration materials and absorbent layers in personal care absorbent products including

disposable diapers, incontinence garments, and feminine care products such as sanitary pads

and napkins, and in face masks, surgical gowns, sterile wraps and surgical drapes.

## DISCUSSION OF THE RELATED ART

Absorbent personal care articles such as sanitary pads and napkins, disposable

diapers, incontinent-care pads and the like are widely used, and much effort has been made

to improve their effectiveness and functionality. These articles generally include a liquid

absorbent material backed by a liquid-imperious barrier sheet. To enhance the sense of

comfort, the absorbent material has a facing of a material which masks at least the body-

facing surface of the product. The purpose of this cover material is to help structurally

contain the absorbent material and to protect the wearer from continuous direct contact with

moisture from previously wetted absorbent material. The cover material is typically of

relatively low basis weight nonwoven fabric. Improved product performance has been

obtained in these products through the incorporation of a surge management material

disposed between the cover material and the absorbent material. The surge management

material is made from a relatively high basis weight, low density, that is, thick, nonwoven

web material.

In nonwoven webs, the fibers comprising the web are generally oriented in the x-y plane of the web and the resulting nonwoven web material is relatively thin, that is lacking in loft or significant thickness. Loft or thickness in a nonwoven web suitable for use in personal care absorbent articles promotes comfort (softness) to the user, surge management and fluid distribution to adjacent layers.

In order to impart loft or thickness to a nonwoven web, it is generally desirable that at least a portion of the fibers comprising the web be oriented in the z-direction. Conventionally, such lofty nonwoven webs are produced using staple fibers. See, for example, U.S. Patent 4,837,067 which teaches a nonwoven thermal insulating batt comprising structural staple fibers and bonding staple fibers which are entangled and substantially parallel to the faces of the batt at the face portions and substantially perpendicular to the faces of the batt, and U.S. Patent 4,590,114 which teaches a batt including a major percent of thermo-mechanical wood pulp fibers stabilized by the inclusion of a minor percent of thermoplastic fibers including staple length thermoplastic fibers. Alternatively, conventional high loft forming processes rely on pre-forming processes such as fiber crimp formed on a flat wire or drum, and post-forming processes such as creping or pleating of the formed web.

#### SUMMARY OF THE INVENTION

In contradistinction to the known art, the present invention does not first form a web of material and pleat it. Rather, fibers are looped on themselves without being first being formed into a material web. These fiber level loops, running from a first major surface of the web to a second major surface, are aggregated in the cross machine direction to form ridged structures herein sometimes called "waves" or "folds" to distinguish them from "pleats" which refer to structures in preformed web or mesh material that has been folded on itself. A "wavelength" may generally be considered the transit of a loop between its successive trough points on one major surface of the web.

Accordingly, it is one object of this invention to provide a lofty nonwoven web material comprising substantially continuous fibers as opposed to staple fibers traditionally used in the manufacture of such nonwoven materials.

It is yet another object of this invention to provide a method for producing nonwoven materials having z-direction orientation portions.

These and other objects of this invention are addressed by a method for producing a material having z-direction folds comprising conveying a substantially unformed and flat base material of substantially continuous fibers, and added materials if desired, on a first moving surface into a nip formed by the first moving surface and a second moving surface, the second moving surface traveling at a slower speed than the first moving surface, resulting in formation of a plurality of z-direction folds on at least one surface of the material. The method of this invention conveys a material by means of a moving surface into a confined space (the nip) and removes it from the confined space by means of a second moving surface, whereby the rate of removal of the material from the confined space is slower than the rate of material input to the confined surface, resulting in formation of a nonwoven material having z-direction components. The z-direction components produce ridges or ripples on both the major, or x-y surfaces of the material. According to this method the extent of the ridges, and thus the character of the resulting material formed, may be easily affected by a number of operating parameters including, but not limited to, the type of material being processed, geometry of the confined space, the means for transferring the material in the confined space from the first moving surface to the second moving surface, presence or lack of a binding agent such as an adhesive, and the relative speeds of the first and second moving surfaces.

Typically, the size of the confined space (nip) and the relative speeds of the moving surfaces are related with respect to the formation of a web having a desired density of folds. For example, for very low differential speeds between the two moving surfaces, the size of the nip will be very small. As the differential speeds increase, the size of the nip will also increase.

According to certain embodiments herein, a material of this invention, as produced with the method of this invention, comprises a nonwoven web with a plurality of substantially continuous fibers having a z-direction orientation and forming a plurality of ridges on the major surfaces of the nonwoven web.

## BRIEF DESCRIPTION OF THE DRAWINGS

These and other objects and features of this invention will be better understood from the following detailed description taken in conjunction with the drawings wherein:

Fig. 1 is a schematic diagram of the method of this invention for producing materials having z-direction components;

Fig. 2 is a diagram of a side view of a nonwoven web having z-direction components in the form of ridges or ripples formed in accordance with the method of this invention;

Figs. 3A and 3B are diagrammatic representations of a conventional nonwoven web and a high loft nonwoven web in accordance with this invention, respectively;

Figs. 4-9 are photographs in side view of nonwoven materials produced in accordance with the method of this invention showing various loop structures.

## DESCRIPTION OF PREFERRED EMBODIMENTS

As used herein, the term "nonwoven web" or "nonwoven material" means a web having a structure of individual fibers, filaments or threads which are interlaid, but not in a regular or identifiable manner such as those in a knitted fabric or films that have been fibrillated. Nonwoven webs or materials have been formed from many processes such as, for example, meltblowing processes, spunbonding processes, and bonded carded web processes. The basis weight of nonwoven webs or materials is usually expressed in ounces of material per square yard (osy) or grams per square meter (gsm), and the fiber diameters usable are usually expressed in microns. (Note that to convert from osy to gsm, multiply osy by 33.91.)

As used herein, the term "z-direction" refers to fibers disposed outside of the plane of orientation of a web. Fig. 3A is a diagram showing a nonwoven web without z-direction fibers. That is, all of the fibers are generally oriented in the direction indicated by arrow 27. By comparison, Fig. 3B is a diagram showing a nonwoven web having z-direction fibers in accordance with this invention. That is, in addition to fibers oriented in the direction of arrow 28, fibers are also oriented in the direction of arrows 29 and 30. The term

"as formed z-direction fibers" as used herein refers to fibers that become oriented in the z-direction during forming of the nonwoven web as distinguished from fibers having a z-direction component resulting from post-forming processing of the nonwoven web, such as in the case of mechanically crimped or creped nonwoven webs.

As used herein, the term "spunbond fibers" refers to small diameter fibers which are formed by extruding molten thermoplastic material as filaments from a plurality of fine, usually circular capillaries of a spinneret as taught, for example, by U.S. Patent 4,340,563 to Appel et al. and U.S. Patent 3,802,817 to Matsuki et al.

As used herein, the term "meltblown fibers" refers to fibers formed by extruding a molten thermoplastic material through a plurality of fine, usually circular, die capillaries as molten threads or filaments into converging high velocity gas streams (for example, airstreams) which attenuate the filaments of molten thermoplastic material to reduce their diameter, which may be to microfiber diameter. Such a process is disclosed, for example, by U.S. Patent 3,849,241 to Butin.

As used herein, the term "microfibers" refers to small diameter fibers having an average diameter not greater than about 75 microns, for example, having an average diameter of from about 0.5 microns to about 50 microns, or more particularly, having an average diameter of from about 2 microns to about 40 microns.

As used herein, the term "polymer" generally includes, but is not limited to, homopolymers, copolymers, such as, for example, block, graft, random and alternating copolymers, terpolymers, etc., and blends and modifications thereof. Furthermore, unless otherwise specifically limited, the term "polymer" also includes all possible geometric configurations of the material. These configurations include, but are not limited to, isotactic, syndiotactic, atactic and random symmetries.

As used herein, the term "personal care absorbent article" means disposable diapers, training pants, absorbent underpants, adult incontinence products, feminine hygiene products and the like.

As used herein, the term "homofilament" refers to a fiber formed from only one polymer. This is not meant to exclude fibers formed from one polymer to which small

amounts of additives have been added for coloration, anti-static properties, lubrication, hydrophilicity, etc.

As used herein, the term "bicomponent fibers" refers to fibers which have been formed from at least two polymers extruded from separate extruders but spun together to form one fiber. Bicomponent fibers are also sometimes referred to as conjugate fibers or multicomponent fibers. Bicomponent fibers are taught by U.S. Patent 5,382,400 to Pike et al.

As used herein, the term "biconstituent fibers" refers to fibers which have been formed from at least two polymers extruded from the same extruder as a blend. The term "blend" is defined below. Biconstituent fibers are sometimes also referred to as multiconstituent fibers. Fibers of this general type are discussed in, for example, U.S. Patent 5,108,827 to Gessner. As used herein, the term "blend" means a mixture of two or more polymers.

As used herein, the term "substantially continuous fibers" refers to fibers, including without limitation, spunbond and meltblown fibers, which are not cut from their original length prior to being formed into a nonwoven web or fabric. Substantially continuous fibers may have average lengths ranging from greater than about 15 centimeters to more than one meter, and up to the length of the web or fabric being formed. The definition of "substantially continuous fibers" includes fibers which are not cut prior to being formed into a nonwoven web or fabric, but which are later cut when the nonwoven web or fabric is cut, and fibers which are substantially linear or crimped.

The term "staple fibers" means fibers which are natural or cut from a manufactured filament prior to forming into a web, and which have an average length ranging from about 0.1-15 centimeters, more commonly about 0.2-7 centimeters.

As used herein, the term "through-air bonding" or "TAB" means the process of bonding a nonwoven, for example, a bicomponent fiber web in which air which is sufficiently hot to melt one of the polymers of which the fibers of the web are made is forced through the web.

As used herein, the term "coform" means a process in which at least one meltblown diehead is arranged near a chute through which other materials are added to the



base material or the web while it is forming. Such other materials may be pulp, superabsorbent particles, cellulose or staple fibers, for example. Coform processes are shown in commonly assigned U.S. Patent 4,818,464 to Lau.

Fig. 1 is a schematic diagram showing the method of this invention for

producing materials including, but not limited to, films, nonwoven materials and woven

materials having z-direction components in the form of ridges or peaks on at least one face.

The ridges or peaks formed in accordance with the method of this invention may be regularly

spaced or irregular in spacing and shape.

As shown in Fig. 1, a base material 21 of lightly, or nonfunctionally, bonded

fibers is transported or conveyed on a first moving surface 11 into the confined space defined

by nip 13 formed by first moving surface 11 and second moving surface 12.

"Nonfunctionally bonded" is a bonding sufficient only to hold the fibers in place for

processing according to the method herein but so light as to not hold the fibers together were

there to be manipulated manually. Such bonding may be incidental or eliminated altogether

if desirable. A coform unit 44 for adding additional materials to the y base material is

attached near the outlet of the fiber distribution unit 16. First moving surface 11 is moving

in the direction of arrow 18 at a given speed. Base material 21 is held down on first moving

surface 11 by a hold down vacuum 14. In nip 13, base material is transferred to second

moving surface 12 moving in the direction indicated by arrow 19 via positive air pressure

from a blow up box 15a underneath first moving surface 11 and a transfer vacuum 20

beneath the second moving surface. The transfer of the material in nip 13 from first moving

surface 11 to second moving surface 12 is accomplished by the application of a transfer

vacuum beneath second moving surface 12 generated by high vacuum slot 15b and a transfer

vacuum represented by reference numeral 20. It will be appreciated that the present

invention may work without a true nip, that is, the first and second surfaces may be serially

offset to such a degree that there is no true overlap in their opposite facing surfaces. Second

moving surface is moving at a speed slower than the speed of first moving surface 11. First

and second moving surfaces are normally foraminous or perforate, wire mesh belts, known

in the art as "wires". In accordance with one preferred embodiment of this invention, the

speed of first moving surface 11 is in the range of about 1.25 to about 7 times faster than the speed of second moving surface 12.

The confining nature of nip 13 is such that, as the base material 21 of fibers enters nip 13 and is taken away at a slower speed by second moving surface 12, base material 21 accumulates in nip 13 causing the fibers to bunch up and translate into a z-direction displacement until the volume of nip 13 is filled. More specifically, base material 21 moving in the direction indicated by arrow 18 encounters a slowdown in nip 13 as a result of which the base material 21 moves in the z-direction until it hits the surface of second moving surface 12 and is removed thereby. As a result, the material exiting from nip 13 comprises at least one surface, and normally both surfaces, having ridges or peaks as indicated by reference numeral 22.

Although suitable for producing ridged films and pleated wovens, the method of this invention is particularly suitable for producing preponderantly open, or low density, nonwoven webs of continuous fibers having z-direction components. Specifically, the material produced in accordance with a preferred embodiment of this invention is a nonwoven web comprising a plurality of substantially continuous fibers having a z-direction orientation and forming the ridges or peaks 22.

The substantially continuous fibers are preferably selected from the group consisting of homofilament fibers, bicomponent fibers and combinations thereof. The substantially continuous fibers are preferably formed with polymers selected from the group consisting of polyolefins, polyamides, polyesters, polycarbonates, polystyrenes, thermoplastic elastomers, fluoropolymers, vinyl polymers, and blends and copolymers thereof.

Suitable polyolefins include, but are not limited to, polyethylene, polypropylene, polybutylene, and the like; suitable polyamides include, but are not limited to, nylon 6, nylon 6/6, nylon 10, nylon 12 and the like; and suitable polyesters include, but are not limited to, polyethylene terephthalate, polybutylene terephthalate and the like. Particularly suitable polymers for use in the present invention are polyolefins including polyethylene, for example, linear low density polyethylene, low density polyethylene, medium density polyethylene, high density polyethylene and blends thereof; polypropylene;

polybutylene and copolymers as well as blends thereof. Additionally, the suitable fiber forming polymers may have thermoplastic elastomers blended therein. In addition, staple fibers may be employed in the nonwoven web as a binder.

In order to provide stability to the product material, the nonwoven web is bonded, either by application of an adhesive from adhesive system 25 or by thermal bonding such as by through-air bonding, a calender, or the like, or by means of a hot air knife (HAK) 24. A hot air knife is used to bond the individual polymer fibers together at various locations so that the web has increased strength and structural integrity for subsequent treatments such as passage through a through-air bonding (TAB) unit. A conventional hot air knife includes a mandrel with a slot that blows a jet of hot air onto the nonwoven web surface. Such hot air knives are taught, for example, by U.S. Patent 5,707,468 to Arnold et al.

As shown in Fig. 1, a base material 21 of substantially continuous fibers is fed onto first moving surface 11 from a Fiber Distribution Unit 16 as at reference numeral 16. However, it will be apparent to those skilled in the art that certain base material 21 fibers may be formed directly on first moving surface 11 or unwound from prewound spools or the like.

Base materials suitable for use in the material and method of this invention are preferably selected from the group consisting of spunbond, meltblown, spunbond-meltblown-spunbond laminates, coform, spunbond-film-spunbond laminates, bicomponent spunbond, bicomponent meltblown, biconstituent spunbond, biconstituent meltblown, pulp, superabsorbent, and combinations thereof.

The characteristics of the material produced in accordance with the method of this invention may be varied by varying such method elements as nip geometry, including the vertical distance between first moving surface 11 and second moving surface 12 as well as the extent of overlap between first moving surface 11 and second moving surface 12, vacuum strength and location, bonding mechanism, and speeds of the material entering and leaving nip 13. The type of fiber will of course have an affect on the morphology of the web made. In addition, although the present invention generally produces a self-supporting lofty web, the end product may include a support structure or a second material 23, as shown being introduced into nip 13 from the unwind designated by reference numeral 17.

Fig. 2 is a diagram showing a side view of a z-direction component nonwoven web 40 produced in accordance with the method of this invention comprising ridges 41 formed by substantially continuous fibers.

Fig. 4 is a photograph of a side view of a nonwoven web produced in accordance with the method of this invention for a 2.5 osy basis weight in which the sheath/core bicomponent straight individual fibers are readily visible showing regularly and elliptically shaped looped fibers at both major surfaces of the web. The web is substantially open and forms a plurality of channels running in the cross machine direction between loops. The loops are oriented off the true z-axis and are unidirectional, i.e. all leaning one way. A nonwoven web according to the present invention has a basis weight preferably in the range of about 0.25 osy to about 50 osy.

Fig. 5 is a photograph of a side view of a nonwoven web produced in accordance with the method of this invention, but at a higher speed differential than Fig. 4, for a 3.0 osy basis weight and in which the substantially continuous individual fibers are readily visible showing slightly more random but still basically elliptically shaped looped fibers at both major surfaces of the web. The web is substantially open, i.e. the fibers are not tightly packed and the web exhibits a preponderance of air spaces rather than fiber at its surfaces, and the web forms a plurality of channels running in the cross machine direction between loops. In terms of gross morphology the material of Fig. 5 will have smoother surfaces and less evident ridges than that of Fig. 4.

Fig. 6 is a photograph of a side view of a nonwoven web produced in accordance with the method of this invention, but with crimped rather than straight fibers, for a 3.2 osy basis weight and in which the substantially continuous individual fibers are readily visible showing even more random, but still basically elliptically shaped looped fibers at both major surfaces of the web. The web is substantially open but does not show distinct channels running in the cross machine direction between loops. In terms of gross morphology the material of Fig. 6 will have broader and less regular ridges, i.e. "regular" referring to the periodicity of pleats in the machine direction and the frequency with which the pleats extend from edge to edge in the cross direction than that of Fig. 5.

Fig. 7 is a photograph of a side view of a nonwoven web produced in accordance with the method of this invention, but at a still higher speed differential, for a 4.0 osy basis weight and in which the looped fibers are highly compressed. The tightly elliptical looped fibers do not show channels between the waves. The web is becoming more closed than open in nature. In terms of gross morphology the material of Fig. 7 will have still smoother surfaces and less evident ridges than those of the previous figures.

Fig. 8 is a photograph of a side view of a nonwoven web produced in accordance with the method of this invention, but at a low 0.5 osy basis weight and in which the substantially continuous individual fibers are readily visible showing quite random waviness to the point of losing the basically elliptically shaped and regular periodicity waviness on the surface of the web. The loops may be considered multi-directional, i.e. leaning at random away from the orthogonal z-axis. The web is very open. In terms of gross morphology the material of Fig. 8 will have smooth surfaces, less evident ridges and many thin spots.

Fig. 9 is a photograph of a side view of a nonwoven web produced in accordance with the method of this invention, but with side by side bicomponent crimped fibers at a low 0.8 osy basis weight again showing quite random waviness. As would be expected, the web shows a lack of regular periodicity waviness on the surface. The web is very open. In terms of gross morphology the material of Fig. 9 will have smooth surfaces, almost nonevident ridges and many thin spots.

In accordance with one preferred embodiment of this invention, the substantially continuous fibers are bicomponent fibers. Particularly suitable polymers for forming the structural component of suitable bicomponent fibers include polypropylene and copolymers of polypropylene and ethylene, and particularly suitable polymers for the adhesive component of the bicomponent fibers includes polyethylene, more particularly linear low density polyethylene, and high density polyethylene. In addition, the adhesive component may contain additives for enhancing the crimpability and/or lowering the bonding temperature of the fibers, and enhancing the abrasion resistance, strength and softness of the resulting webs.

The nonwoven web of the material of this invention has a basis weight in the range of about 0.25 oz/y to about 50 oz/y. To enhance the absorption characteristics of the nonwoven material, in accordance with one embodiment of this invention, the nonwoven web comprises an absorbent, for example, superabsorbent particles. In accordance with one embodiment of this invention, a support structure is attached to at least one face of the nonwoven web so as to provide strength thereto. The resulting laminate structure provides support for the high loft structure, strength for winding, converting, etc., and a boundary layer to either enhance or retard fluid flow into the lofty absorbent structure. The support structure may include spunbond webs of various types including liners, perforated, micro-fiber, creped, etc., spunbond-meltblown-spunbond (SMS), meltblown, and/or films.

Potential applications for the nonwoven web of this invention include personal care absorbent articles such as diapers, training pants, incontinence garments, feminine care products including sanitary pads and napkins, all surge materials, loop for hook and loop, air filtration, liquid filtration, body scrub pads, oil sorb, industrial and baby wipes, insulation material, packaging material, and translucent or shading material for lamp shades or the like. In the case of filtration materials, the method of this invention greatly increases the surface area available for filtration. In addition, the method of this invention may be suitable for pleating fabrics. And, for rolls of diapers, a composite material could be produced by ridging or ruffling a high loft surge/pulp/superabsorbent material laminate and placing it in between an outer cover and a liner, which would produce a laminate with all of the components of a diaper in a single step, which could be wound up and cut and placed later on converting machines.

While in the foregoing specification this invention has been described in relation to certain preferred embodiments thereof, and many details have been set forth for purpose of illustration, it will be apparent to those skilled in the art that the invention is susceptible to additional embodiments and that certain of the details described herein can be varied considerably without departing from the basic principles of the invention.

## WE CLAIM:

1. A material comprising:
  1. a nonwoven web comprising a plurality of substantially continuous fibers having a z-direction orientation and forming a plurality of ridges on both surfaces of the nonwoven web.

2. The lofty material of claim 1 further comprising:
  - the nonwoven web being a lofty web with x, y and z dimensions, with x being the machine direction, y being the cross machine direction and z being the loft direction;
  - first and second major surfaces in x-y planes and spaced apart in the z direction;
  - the continuous fibers being folded to form loops extending in the z direction and the loops combining to form a material with a succession of waves spaced along the machine direction, each wave running in the cross machine direction.

3. The material according to Claim 2 further including each wave having at least one of its leading or trailing edges bonded to an adjacent leading or trailing edge to thereby hold its z-direction shape.

4. The material according to Claim 3 wherein the leading and trailing edges of one wave are bonded together.

5. The material according to Claim 3 wherein the leading and trailing edges of one wave are bonded together and bonded to the trailing and leading edges of the adjacent waves, respectively.

6. The material according to Claim 2 further including each wave being substantially elliptically shaped in cross section between the major surfaces.

7. The material according to Claim 2 further including: the waves are oriented off the orthogonal z- axis and are unidirectional.
8. The material according to Claim 2 further including: the waves are oriented off the orthogonal z- axis and are multi-directional.

9. The material according to Claim 2 further including: the first major surface being preponderantly closed.

10. The material according to Claim 2 further including: the second major surface being preponderantly closed.

11. The material according to Claim 2 further including: the waves being randomly spaced in the machine direction.

12. The material according to Claim 2 further including: the waves being regularly spaced in the machine direction.

13. The material according to Claim 2 further including: the waves being random length in the cross machine direction.

14. The material according to Claim 2 further including: the waves being regular length in the cross machine direction.

15. The material according to Claim 14 wherein: the waves extend from edge to edge in the cross machine direction.

16. A material in accordance with Claim 1, wherein the substantially continuous fibers are selected from the group consisting of spunbond, meltblown and combinations thereof.



17. A material in accordance with Claim 1, wherein the substantially continuous fibers comprise an adhesive.

18. A material in accordance with Claim 1, wherein the substantially continuous fibers are thermally bonded.

19. A material in accordance with Claim 1, wherein the nonwoven web has a basis weight in a range of about 0.25 osy to about 50 osy.

20. A material in accordance with Claim 1, wherein the substantially continuous fibers are polymeric fibers.

21. A material in accordance with Claim 20, wherein the polymeric fibers are thermoplastic fibers.

22. A material in accordance with Claim 1, wherein the substantially continuous fibers are selected from the group consisting of homofilament fibers, bicomponent fibers, biconstituent fibers and combinations thereof.

23. A material in accordance with Claim 1, wherein a support structure is attached to at least one face of the nonwoven web.

24. A material in accordance with Claim 1, wherein the nonwoven web further comprises an absorbent.

25. A method for producing a material having z-direction folds comprising:  
 conveying continuous fibers on a first moving surface from a first moving surface to a second moving surface, the second moving surface traveling at a slower speed than the first moving surface, resulting in formation of a material having a plurality of z-direction folds on both surfaces of the material.

26. The method for producing a material having z-direction folds according to claim 25 further comprising:  
 positioning the first moving surface and the second moving surface to form a nip therebetween.

27. A method in accordance with Claim 25 wherein the continuous fibers are selected from the group consisting of spunbond, meltblown, spunbond-meltblown-spunbond laminates, coform, spunbond-film-spunbond, bicomponent spunbond, bicomponent meltblown, bicomponent spunbond, bicomponent meltblown, and combinations thereof.

28. A method in accordance with Claim 25, wherein the first moving surface is traveling in a range of about 1.25 to about 7 times faster than the second moving surface.

29. A method in accordance with Claim 25, wherein the first moving surface is a forming surface on which the fibers are formed.

30. A method in accordance with Claim 25 wherein the fibers are lightly bonded.

31. A method in accordance with Claim 25, wherein the nonwoven material is bonded by at least one of an adhesive bonding process and a thermal bonding process.

32. A method in accordance with Claim 25, wherein the first moving surface and the second moving surface are perforate.

33. A method in accordance with Claim 32, wherein the material is transferred from the first moving surface to the second moving surface using a controlled vacuum whereby the material is pulled in a direction of the second moving surface.

34. A method in accordance with Claim 33, wherein the material is transferred from the first moving surface to the second moving surface using a positive air pressure whereby the material is pushed in a direction of the second moving surface.

35. A method in accordance with Claim 25, wherein at least one additional material is applied to a face of the base material, forming a composite or laminate.

36. A method in accordance with Claim 25 wherein the first moving surface and second moving surface face opposing directions.

37. A method in accordance with Claim 36 wherein the first moving surface and second moving surface have no directly opposing faces to form a channel.

38. A method in accordance with Claim 25, wherein the continuous fibers comprise a plurality of thermoplastic fibers

39. A personal care absorbent article comprising:

a nonwoven web comprising a plurality of substantially continuous fibers having a z-direction orientation and forming a plurality of ridges on both surfaces of the nonwoven web.

40. A personal care absorbent article in accordance with Claim 39, wherein the nonwoven web further comprises an absorbent.

41. A filtration material comprising: a nonwoven web comprising a plurality of substantially continuous fibers having a z-direction orientation and forming a plurality of ridges on at least one surface of the nonwoven web.

42. A filtration material in accordance with Claim 41, wherein a support structure is attached to at least one face of the nonwoven web.






FIG. 3B







FIG. 3A  
PRIOR ART



Rush Transfer (on-line)  
2.5 osy, S/C "straight" Fibers



FIG. 4



Rush Transfer (on-line) 3.0 osy



FIG. 5

Rush Transfer (on-line) 3.2 osy



FIG. 6

High Rush SB Rush Transfer (on-line) 4 osy



FIG. 7

Rush Transfer (on-line) 0.5 osy




FIG. 8

Rush Transfer (on-line)  
08 osy, S/S "crimped" Fibers




FIG. 9

## INTERNATIONAL SEARCH REPORT

Int'l Application No  
PCT/US 00/10758A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 A61F13/15 004H3/16  
B65H45/06 004H13/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 A61F 004H B65H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category \*  
Citation of document, with indication, where appropriate, of the relevant passages  
Relevant to claim No.

X	EP 0 137 644 A (PERSONAL PRODUCTS CO) 17 Apr 11 1985 (1985-04-17)	1-5, 12, 14-27, 29-31, 35-40
A	US 5 658 640 A (OLSON DAVID A ET AL) page 9, line 15 - line 23; example 1 page 13, line 22 - column 14, line 5 page 17, line 28 - page 18, line 18	25-28, 30, 35-38, 41, 42
A	US 5 021 050 A (ISKRA MICHAEL J) 4 June 1991 (1991-06-04) column 4, line 63 - column 6, line 47; example 1	1, 25-31, 35, 38-40
	--- -/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document relating to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other documents, such combination being obvious to a person skilled in the art
- "Z" document member of the same patent family

Date of the actual completion of the international search

16 August 2000

Date of mailing of the international search report

24/08/2000

Authorized officer

V Beurden-Hopkins, S

Name and mailing address of the ISA  
European Patent Office, P.B. 5816 Patankaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

# INTERNATIONAL SEARCH REPORT

Int. Patent Application No  
PCT/US 00/10758

C: (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
------------	--	-----------------------

A	US 4 111 733 A (PERIERS GILBERT) 5 September 1978 (1978-09-05) column 6, line 49 - column 8, line 59	1,25
A	EP 0 295 038 A (MINNESOTA MINING & MFG) 14 December 1988 (1988-12-14) cited in the application page 5, line 1 - line 8	7

## INTERNATIONAL SEARCH REPORT

Information on patent family members

Inventor: Apple Inc.  
PCT/US 00/10758

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
---	---------------------	----------------------------	---------------------

EP 0137644	A	US	4578070 A	25-03-1986
		AT	55238 T	15-08-1990
		AU	565232 B	10-09-1987
		AU	3190284 A	21-02-1985
		BR	8404038 A	16-07-1985
		CA	1226120 A	01-09-1987
		DE	3482928 D	13-09-1990
		DK	390084 A	16-02-1985
		FI	843203 A, B,	16-02-1985
		GB	2145126 A, B,	20-03-1985
		GR	79970 A	31-10-1984
		HK	99386 A	24-12-1986
		IE	55605 B	21-11-1990
		JP	2096329 C	02-10-1996
		JP	7121270 B	25-12-1995
		JP	60052603 A	25-03-1985
		KR	9103223 B	24-05-1991
		MX	172130 B	06-12-1993
		MY	28987 A	31-12-1987
		NO	843242 A, B,	18-02-1985
		NZ	209139 A	30-10-1987
		NZ	221338 A	28-10-1988
		PH	22505 A	12-09-1988
		PT	79069 A, B	01-09-1984
		SG	75586 G	27-02-1987
		ZA	8406312 A	26-03-1986
		CA	1253320 A	02-05-1989
		MX	161113 A	31-07-1990
		CA	1253319 A	02-05-1989

US 5658640	A	US	5643507 A	01-07-1997
		US	5641555 A	24-06-1997
		US	5658641 A	19-08-1997
		BR	9407288 A	01-10-1996
		CA	2166612 A	23-02-1995
		DE	69406547 D	04-12-1997
		DE	69406547 T	10-06-1998
		EP	0715536 A	12-06-1996
		JP	9501746 T	18-02-1997
		WO	9505232 A	23-02-1995

US 5021050	A	WO	9108717 A	27-06-1991
US 4111733	A	NONE		

EP 0295038	A	US	4837067 A	06-06-1989
		CA	1295471 A	11-02-1992
		CN	1013970 B	18-09-1991
		DE	3883088 A	16-09-1993
		DE	3883088 T	10-03-1994
		HK	101094 A	30-09-1994
		JP	2595044 B	26-03-1997
		JP	63309658 A	16-12-1988
		KR	9601405 B	27-01-1996
		MX	166234 B	24-12-1992
		PT	87579 A, B	31-05-1989